

Applicable interface: cement mortar surfaces, gypsum boards, concrete surfaces

Steps	Apply material	Add water ratio	Apply method	Coverage(one time)	Remark
1	Special matching primer (22KG white primer + Pigment)	15-20%	Rolling/Praying	170-220m ²	
Construction interval	2~4h(20-25°C)				
2	Special matching primer (22KG white primer + Pigment)	15-20%	Rolling/Praying	170-220m ²	
Construction interval	Over 24h(20-25°C)				
3	Stone Paint 25KG	0-5%	Spraying	14-16m ²	Use a dedicated spray gun for spraying. The air compressor pressure should reach at least 7 kg/m ³ . The nozzle must be perpendicular to the wall, and the nozzle should be approximately 50-80 cm away from the wall during spraying.
Construction interval	Over 24h(20-25°C)				
4	Stone Paint 25KG	0-5%	Spraying	14-16m ²	Use a dedicated spray gun for spraying. The air compressor pressure should reach at least 7 kg/m ³ . The nozzle must be perpendicular to the wall, and the nozzle should be approximately 50-80 cm away from the wall during spraying.
Construction interval	24-48h				
Polish	Use 240#-320# sand paper				
5	Exterior Topcoat 18KG	15-20%	Rolling	180-216m ²	
Construction interval	4-6h				
6	Exterior Topcoat 18KG	15-20%	Rolling	180-216m ²	
Dry time	48h fully cured				