

Applicable interface: cement mortar surfaces, gypsum boards, concrete surfaces

Steps	Apply material	Add water ratio	Apply method	Coverage(one time)	Remark
1	Alkali-resistant Primer 18KG	15-20%	Rolling/Praying	170-220m ²	
Construction interval	20-25°C 2~4h				
2	Alkali-resistant Primer 18KG	15-20%	Rolling/Praying	170-220m ²	
Construction interval	20-25°C24h以上				
3	Italian Spray Paint 20KG + Pigment	5-8%	Spraying	20-30m ²	Use a stone paint spray gun, keeping the nozzle perpendicular to the wall and approximately 50cm away from the wall during spraying.
Construction interval	24-48h				
4	Exterior Topcoat 18KG	15-20%	Rolling	180-216m ²	
Construction interval	4-6h				
5	Exterior Topcoat 18KG	15-20%	Rolling	180-216m ²	
Dry time	24h				