

Microcement - Sealer



Sealer

Vanlei Sealer is a water-based sealant that acts as a bonding bridge between the microcement and the topcoat, consolidating the microcement coating.

01. *Main Ingredients*

Acrylic resin

02. *Product Features*



A. Consolidates microcement coatings



B. Moisture and alkali resistant



C. High adhesion



D. Easy to apply

03. *Scope of application*

✓ Suitable for interior/exterior walls. Suitable for walls, floors and ceilings.

04. Complementary system



✓ Microcement



✓ Emulsion



✓ Primer



✓ Sealer



✓ Topcoat



✓ Microcement curing agent

05. Technical parameters

Material Properties	Solvent-free (water-based)
Dry film thickness	100-150µm

Drying time (surface drying)	<2h(25-27°C)
Drying time (hard)	>24h(25-27°C)
Coating layer	1 times
Service life	> 10 years
Paint color	Transparent
Storage	5-35°C, cool, dry
Net Weight	5kg
Package	
bucket size	18.5*14.5*31.5cm



Reference Dosage : 5-6m²/kg



Tools : wool roller



wool roller

06. Substrate requirements

- ① The base layer should be flat, clean, free of oil, hollow, and have good strength before construction
 - ② Renovation of old walls: level the base, remove loose surface parts, clean dust, grease and other impurities before construction.
-

07. Construction method



01. Direct roller coating

08. Shelf life

12 months in a dry state at room temperature (at the time of original shipment)

09. Implementation Standard

JG/T 210-2018 Primer for interior and exterior wall

10. Environmental commitment

This product does not add any heavy metals and other harmful substances, does not exceed the latest national standards for the limit of harmful substances in interior decoration materials, and is fully in line with the technical requirements of China's environmental products.

11. Precautions

- 1、 Read the construction instructions of the package before use to get reliable and satisfactory painting effect.

- 2、 Please effectively separate, cover and shield the area of wood products and walls.
 - 3、 Temperature lower than 10 °C, relative humidity greater than 80 % can not be constructed.
 - 4、 The freshly scraped surface should try to avoid direct exposure to strong sunlight, strong wind and rain, so as not to cause surface cracks and reduce strength.
-

12. *Technical support*

For assistance, please consult Wanlei (0757-81760676).



WeChat Official Account



WeChat mini program