

Applicable interface: cement mortar surfaces, gypsum boards, concrete surfaces

Steps	Apply material	Add water ratio	Apply method	Coverage(one time)	Remark
1	Anti-alkali Sand Primer 22KG	15-20%	Rolling	65-90m²	
Construction interval	2~4h(20-25°C)				
2	Anti-alkali Sand Primer 22KG	15-20%	Rolling	65-90m²	
Construction interval	Over 24h(20-25°C)				
3	Gamazine Paint 25kg	3-5%	Scraping	24-30m²	
Construction interval	12-24h				
4	Gamazine Paint 25kg	3-5%	Scraping	24-30m²	While applying the coating, use an acrylic scrubbing board to irregularly rub in circular motions. Once it's semi-dry, use the acrylic scrubbing board again to create a textured finish.
Construction interval	24-48h				
Polish	Use 320# sand paper				
5	Semi-gloss scratch resistant topcoat 5kg	15-20%	Rolling	50m²	
Construction interval	4-6h				
6	Semi-gloss scratch resistant topcoat 5kg	15-20%	Rolling	50m²	
Dry time	24h				