Suitable for: Interior walls. Used for wall decoration, especially for large areas.

Steps	Apply material	Add water ratio	Apply method	Tool	Coverage(one time)	Remark	
1	Penetrant primer18KG	20-25%	Rolling	Wool roller	210-250㎡	Using a short-nap roller, apply a small amount of material evenly to the surface to be coated, ensuring complete coverage.	
Construction interval	Standard room temperature（20–25℃）：4-6 h，Summer（30–35℃）：2-4 h，Winter（5–10℃）：12–24 h						
2	Penetrant primer18KG	20-25%	Rolling	Wool roller	210-250㎡	Using a short-nap roller, apply a small amount of material evenly to the surface to be coated, ensuring complete coverage.	
Construction interval	Standard room temperature（20–25℃）：8-10 h，Summer（30–35℃）：6-8h，Winter（5–10℃）：12–24 h						
3	Cloudy Metallic (Main material) 10kg	3-5%	Scraping	Trowel	50-70㎡	Apply a coat of plaster to the main material	
Construction interval	Standard room temperature（20–25℃）：8-10 h，Summer（30–35℃）：6-8h，Winter（5–10℃）：12–24 h						
Polish	Use 320# sand paper						
4	Cloudy Metallic (Main material) 10kg	3-5%	Scraping	Trowel	50-70㎡	Apply one coat of plaster to the main material, with a thickness of no more than 1mm.	
Construction interval	Standard room temperature（20–25℃）：8-10 h，Summer（30–35℃）：6-8h，Winter（5–10℃）：12–24 h						
Polish	Use 1000# sand paper						
5	Cloudy Metallic (Wax 1) 5kg	40-50%	Rubbing	Square sponge	60-80㎡	Apply evenly in circular motions with a square sponge.	First, dampen the sponge, then wring out the excess water, and then dip it in the paint and apply it.
Construction interval	Standard room temperature（20–25℃）：4-6 h，Summer（30–35℃）：2-4 h，Winter（5–10℃）：8-12 h						
6	Cloudy Metallic (Wax 1) 5kg	40-50%	Rubbing	Square sponge	60-80㎡	Apply evenly in circular motions with a square sponge.	First, dampen the sponge, then wring out the excess water, and then dip it in the paint and apply it.
Construction interval	Standard room temperature（20–25℃）：8-10 h，Summer（30–35℃）：6-8h，Winter（5–10℃）：12–24 h						
Polish	Use 1000# sand paper						
7	Cloudy Metallic (Wax 2) 2.5kg	100%	Rubbing	Square sponge	50-75㎡	Apply evenly in circular motions with a square sponge.	First, dampen the sponge, then wring out the excess water, and then dip it in the paint and apply it.
Construction interval	Standard room temperature（20–25℃）：4-6 h，Summer（30–35℃）：2-4 h，Winter（5–10℃）：8-12 h						
8	Cloudy Metallic (Wax 2) 2.5kg	100%	Rubbing	Square sponge	50-75㎡	Apply evenly in circular motions with a square sponge.	First, dampen the sponge, then wring out the excess water, and then dip it in the paint and apply it.
Construction interval	Standard room temperature（20–25℃）：4-6 h，Summer（30–35℃）：2-4 h，Winter（5–10℃）：8-12 h						
9	Cloudy Metallic (Wax 2) 2.5kg	100%	Rubbing	Square sponge	50-75㎡	Apply evenly in circular motions with a square sponge.	First, dampen the sponge, then wring out the excess water, and then dip it in the paint and apply it.
Construction interval	Standard room temperature（20–25℃）：8-10 h，Summer（30–35℃）：6-8h，Winter（5–10℃）：12–24 h						
10	Interior Topcoat 5kg	20-25%	Rubbing	Square sponge	100-150㎡	Apply evenly in circular motions with a square sponge.	First, dampen the sponge, then wring out the excess water, and then dip it in the paint and apply it.
Construction interval	Standard room temperature（20–25℃）：4-6 h，Summer（30–35℃）：2-4 h，Winter（5–10℃）：8-12 h						
11	Interior Topcoat 5kg	20-25%	Rubbing	Square sponge	100-150㎡	Apply evenly in circular motions with a square sponge.	First, dampen the sponge, then wring out the excess water, and then dip it in the paint and apply it.
Dry time	Standard room Temperature（20–25℃）：people can stand 24 h fully cured 7 days						