Suitable spaces: Interior walls of high-end banquet halls, luxury boutiques, upscale villas, hotels, etc.

Steps	Apply material	dd water rati	Apply method	Tool	Coverage(one time)	Construction Method	Remark
1	Anti-alkali Sand Primer 5KG/ Interior white primer 5KG	20-25%	Rolling	wool roller	15-20㎡ / 50-60㎡	Using a short-nap roller, pick up a small amount of material and apply it evenly to the surface, ensuring complete coverage.	
Construction interval	8-12h						
2	Anti-alkali Sand Primer 5KG/ Interior white primer 5KG	20-25%	Rolling	wool roller	15-20㎡ / 50-60㎡	Using a short-nap roller, pick up a small amount of material and apply it evenly to the surface, ensuring complete coverage.	
Construction interval	Over 24h						
3	Metal Velvet 4KG	10-15%	Rolling	wool roller	36-48㎡	For the metal velvet base coat, use a short-nap roller to pick up a small amount of material and apply it evenly to the surface, ensuring complete coverage.	
Construction interval	8-12h						
4	Metal Velvet 4KG	8-12%	Rolling+ Rubbing	wool roller + velvet sanding pad	36-48㎡	Apply the metallic velvet base material by roller coating, simultaneously using a velvet sander to create the texture in circular motions. After it is semi-dry, refine the texture as needed.	
Construction interval	8-12h						
5	Metal Velvet 4KG	8-12%	Rolling+ Rubbing	wool roller + velvet sanding pad	36-48㎡	Apply the metallic velvet base material by roller coating, simultaneously using a velvet sander to create the texture in circular motions. After it is semi-dry, refine the texture as needed.	
Dry time	24h						