Suitable Substrates: Absorbent substrates, including concrete, cement, putty, and similar surfaces.

Steps	Apply material	Add water ratio	Apply method	Coverage(one time)	Remark
1	Acid-proof Primer 2kg	30%	Rolling	24㎡	
Construction interval	4-6h				
2	Acid-proof Primer 2kg	30%	Rolling	24㎡	
Construction interval	4-6h				
3	Rust paint 6kg	/	Rolling	36-48㎡	If the material is too thick, add 3–5% water
Construction interval	4-6h				
4	Rust paint 6kg	/	Rolling	36-48㎡	If the material is too thick, add 3–5% water
Construction interval	4-6h				
5	Copper rust paint 4kg	/	Dab	24-32㎡	If the material is too thick, add 3–5% water
Construction interval	4-6h				
6	Copper rust paint 4kg	/	Dab	24-32㎡	If the material is too thick, add 3–5% water
Construction interval	At about 60% dry, roll or dab on the Oxidizing Agent.				
7	Oxidizing agent 1kg	/	Rolling/Dab	6㎡	
Construction interval	24h				
Polish	Sand with 240–320 grit sandpaper				
8	FU Topcoat 2kg	15-20%	Rolling/Spray	24㎡	
Construction interval	4-6h				
9	FU Topcoat 2kg	15-20%	Rolling/Dab	24㎡	
Dry time	24h				