Application: Suitable for indoor use. Continuous indoor floor coatings; Flooring systems with a properly leveled mortar base.

Steps	Apply material	Add water ratio	Apply method	Tool	Coverage(one time)	Construction Method	Remark
1	Terraprimer：A 3kg +Terraprimer：B 1kg	/	Trowelling	finishing trowel	24-32㎡	After thoroughly mixing the primer, apply it to the surface to be treated, ensuring complete coverage of the entire	
Construction interval	24-48h						
2	Terraprimer：A 3kg +Terraprimer：B 1kg	/	Trowelling	finishing trowel	24-32㎡	After thoroughly mixing the primer, apply it to the surface to be treated, ensuring complete coverage of the entire	
Construction interval	24-48h						
3	Terrafiller：A 10kg +Terrafiller：B 2kg	/	Trowelling	3–5 mm serrated trowel	10-12㎡	After thoroughly mixing Terrafiller, apply it evenly over the entire surface using a 3–5 mm serrated trowel, ensuring full and complete coverage.	
Construction interval	24-48h						
Polish	Grind using a floor grinding machine.						
4	Terrazzino：A 10kg + component B 2kg + component C 4kg	/	Trowelling +Rolling	3–5 mm serrated trowel + spiked roller	Fine sand：7.2-8.8㎡ Coarse sand：5.4-6.4㎡	Pour the mixed Terrazzino onto the surface to be coated, and spread it evenly using a 3–5 mm serrated trowel, ensuring complete coverage over the entire area. Then, use a defoaming roller on the applied Terrazzino to help eliminate air bubbles, thereby ensuring the floor’ s flatness and compaction.	1. Upon opening the Terrazzino container, first mix components A and B thoroughly in the specified ratio. Do not add water. After complete mixing, add component C and stir uniformly for about 5 minutes. (The mixed material must be used within 30 minutes.) 2. If color addition is required, first mix the pigment evenly into component A before combining it with component B.
Dry time	Allow to dry for 24h; no topcoat is required (full curing takes 24–48h).						