Suitable surfaces: floor tiling, garden landscaping, and furniture countertops

Steps	Apply material	Add water ratio	Apply method	Coverage(one time)	Remark
1	Epoxy primer 4.5kg + Epoxy Hardener 0.5kg	10%	Rolling	40-60㎡	When applying to absorbent substrates, the water ratio can reach up to 40%.
Construction interval	12-24h				
2	Resin Floor Stone 20kg + Polyurea Resin A 750g + Polyurea Resin B 250g	/	Scraping	1-3mm：10-12kg/㎡ 3-5mm：15-17kg/㎡	First, mix components A and B together, add them to the main ingredient and mix thoroughly. Must be used within one hour of mixing.
Construction interval	24h				
Dry time	Avoid rain within 12 hours after construction. At 25℃, the surface will dry in 8-12 hours or more, and the internal and external drying time will be 72 hours (the final drying time depends on the temperature).				